

Soarnol®

ETHYLENE-VINYLAICOHOL COPOLYMER




V2603

V2603B

26 mol% Ethylene Content





[General Description]

Soarnol V2603(B) is one of the standard grades of “Soarnol®”, its ethylene content is 26 mol% with a low MFR(melt flow rate).

Soarnol V2603(B) is truly a unique EVOH with the best gas barrier property at normal humidity of all commercial EVOH resins. It is suited for coextruded blow-molded containers as well as coextruded sheet, coextruded film and coextrusion coating.

[General Properties]


<i>Property</i>	<i>Unit</i>	<i>Value</i>
Ethylene Content	mol%	26
MFR ¹⁾ (@210deg C, 2160g)	g/10min	3.2
Volatile Matter	%	< 0.3
Melting Point ²⁾	deg C	195
Crystallization Temperature ²⁾	deg C	171
Oxygen Permeability ³⁾	cc 20 μ m / m ² day atm	0.3
20deg C-50%RH	cc·mil/100inch ² ·day·atm	0.015
WVTR	g 30 μ m / m ² 24hrs	37-70
40deg C-90%RH		

1): Measured with Melt Indexer

2): Measured with DSC, both heating and cooling speeds of 10deg C /min

3): Measured with OXTRAN 10/50 (MOCON)





[Melt Viscosity]




Fig.1 Melt Viscosity of Soarnol V2603(B)


[Example of Processing]

- Extruder: 40 mm ϕ single screw extruder, L/D = 28
- Screw: Full-flighted, constant pitch type, CR = 3.5
- Screen pack: 80/120/50 mesh
- Die: Manifold type, die width = 450 mm, lip clearance = 0.2 mm

Processing Temperature: deg C(deg F)

C ₁	C ₂	C ₃	C ₄	C ₅	Head	Die
180	200	220	230	230	230	200-220
(356)	(392)	(428)	(446)	(446)	(446)	(392-428)





[Hygienic Performance of Soarnol V2603(B)]

Soarnol V2603(B) contains no heavy metals or other harmful substances.
Soarnol V2603(B) meets the Food Sanitation Standards of various countries.

Japan: Ministry of Health and Welfare Announcement No.370(Dec. 28,1959)
and Its Latest Amendment No.18(Jan. 31,1994)

Self-Restrictive Requirements on Food-Contacting Articles

Made of Polyolefins and Certain Polymers

U.S.A.: FDA 21CFR 177.1360(a)(3) and 175.105

E U: European Commission Directive 90/128/EEC,
and Its Latest Amendment

Date Revised: Sep. 1, 2003

The Nippon Synthetic Chemical Industry Co., Ltd

Head Office	:	Umeda Sky Building, 1-88, Oyodonaka 1-chome, Kita-ku, Osaka 531-6029, Japan	TEL 81-6-6440-5313	FAX 81-6-6440-5326
Tokyo Office	:	Nittobo Building, 8-1, Yaesu 2-chome, Chuo-ku, Tokyo 104-0028, Japan	TEL 81-3-3273-1388	FAX 81-3-3273-3029
Nagoya Office	:	Dainagoya Building, 28-12, Meieki 3-chome, Nakamura-ku, Nagoya 450-0002, Japan	TEL 81-52-565-3538	FAX 81-52-565-3574
Central Research Laboratory	:	13-1, Muroyama 2-chome, Ibaraki, Osaka 567-0052, Japan	TEL 81-726-43-2256	FAX 81-726-43-2257
Kyushu Office	:	Daihaku Center Building, 19-24, Hakata-Ekimae 2-chome, Hakata-ku, Fukuoka 812-0011, Japan	TEL 81-92-432-0104	FAX 81-92-432-0122
Processing-Technique Development Center	:	8-1, Matsue 4-chome, Kurashiki, Okayama 712-8052, Japan	TEL 81-86-455-5214	FAX 81-86-455-5289
NIPPON GOHSEI Europe GmbH	:	Merowingerplatz 1a, D-40225, Düsseldorf, Germany	TEL 49-211-385488-0	FAX 49-211-385488-29
NIPPON GOHSEI UK Ltd.	:	Unit 14 Marina Court, Castle Street, Hull HU1 1TJ, UK	TEL 44-1482-333320	FAX 44-1482-333325
NOLTEX L.L.C.	:	12220 Strang Road, La Porte TX 77571-9740, USA	TEL 1-281-842-5000	FAX 1-281-842-5095
SOARUS L.L.C.	:	3930 Ventura Drive, Suite 440 Arlington Heights, IL 60004, USA	TEL 1-847-255-1211	FAX 1-847-255-4343

URL: <http://www.soarnol.com/>
<http://www.nichigo.co.jp/>

