



Hydrogen Gas Barrier Property of “Soarnol[®]”

Hydrogen gas barrier property of “Soarnol[®]” is shown in the following.

Condition : 23deg C,Dry Film, Differential Pressure Method
(JIS K7126 A method)

Sample	Hydrogen Gas Permeability (cc 20 μ m/m ² day atm)
Soarnol 29mol%	27
Soarnol 32mol%	32
Soarnol 44mol%	195
OPP	11,000

Data Prepared : 1 Sep. 2003

