



Organic Solvent Barrier Property of “Soarnol[®]”

Organic solvent barrier property of “Soarnol[®]” is shown in the following.

Sample	Thickness (μ m)	Permeability (mg/cm ² ·day) at 20deg C			
		Chloroform	Xylene	MEK	Kerosene
Soarnol 44mol%	20	0.31	0.14	0.48	<0.005
Soarnol 32mol%	20	0.20	0.11	0.39	<0.005
ONy	25	1.35	0.09	0.26	0.03
PET	25	31.00	0.17	0.16	0.05
KON	15	0.87	0.08	0.16	<0.005

Data Prepared : 1 Sep. 2003

